



TYPICAL PROPERTIES	TEST RESULTS	ASTM
SPECIFIC GRAVITY	1.24	(D792)
DUROMETER HARDNESS, 10 SEC. DELAY	80A	(D2240)
TENSILE STRENGTH	2600 PSI	(D412)
ULTIMATE ELONGATION	360%	(D412)
GRAVES TEAR STRENGTH	260 PPI	(D1004)
100% MODULUS	1360 PSI	(D412)
UV RESISTANCE	YES	
LOW TEMPERATURE BRITTLENESS	-36° F / -38° C	(D746)
OPERATING TEMPERATURE	0° F TO 150° F	
FLAMMABILITY	PASS	U.L. 94 V-0
FLAMMABILITY	PASS	N.F.P.A. 701

IMPORTANT: COMPLETE TEST RESULTS FOR OUTGASSING, ANTI-STATIC AND FLAME SPREAD AVAILABLE UPON REQUEST. WE BELIEVE THESE TESTS TO BE RELIABLE AND ACCURATE TO THE BEST OF OUR KNOWLEDGE BUT CANNOT WARRANTY FOR PROCESSES AND APPLICATIONS BEYOND OUR CONTROL.